

M924 Application Guide – Speed & Feed (inch)

ISO Code	Work Material	Type of Cut	Axial DOC	Radial DOC	Number of Flutes	Speed (SFM)	Feed (Inches per Tooth)											
							1/8	5/32	3/16	7/32	1/4	5/16	3/8	7/16	1/2	5/8	3/4	1
K	Cast Iron Gray	Slotting	1 x D	1 x D	4	325	.0006	.0008	.0009	.0011	.0012	.0015	.0018	.0021	.0024	.0030	.0036	.0048
		Peripheral - Rough	1.25 x D	.5 x D	4	400	.0008	.0009	.0011	.0013	.0015	.0019	.0023	.0026	.0030	.0038	.0045	.0060
			Finish	1.5 x D	.015 x D	4	475	.0008	.0010	.0012	.0014	.0017	.0021	.0025	.0029	.0033	.0041	.0050
	Cast Iron Ductile	Slotting	1 x D	1 x D	4	300	.0006	.0007	.0008	.0010	.0011	.0014	.0017	.0019	.0022	.0028	.0033	.0044
		Peripheral - Rough	1.25 x D	.5 x D	4	375	.0007	.0008	.0010	.0012	.0014	.0017	.0020	.0024	.0027	.0034	.0041	.0054
			Finish	1.5 x D	.015 x D	4	450	.0008	.0009	.0011	.0013	.0015	.0019	.0023	.0026	.0030	.0038	.0045
	Cast Iron Malleable	Slotting	.75 x D	1 x D	4	250	.0006	.0007	.0008	.0010	.0011	.0014	.0017	.0019	.0022	.0028	.0033	.0044
		Peripheral - Rough	1.25 x D	.5 x D	4	325	.0007	.0008	.0010	.0012	.0014	.0017	.0020	.0024	.0027	.0034	.0041	.0054
			Finish	1.5 x D	.015 x D	4	400	.0008	.0009	.0011	.0013	.0015	.0019	.0023	.0026	.0030	.0038	.0045
P	Low Carbon Steels 1018, 12L14, 8620	Slotting	1 x D	1 x D	4	350	.0007	.0008	.0010	.0011	.0013	.0016	.0020	.0023	.0026	.0033	.0039	.0052
		Peripheral - Rough	1.25 x D	.5 x D	4	425	.0008	.0010	.0012	.0014	.0016	.0020	.0024	.0028	.0032	.0040	.0048	.0064
			Finish	1.5 x D	.015 x D	4	500	.0009	.0011	.0014	.0016	.0018	.0023	.0027	.0032	.0036	.0045	.0054
	Medium Carbon Steels 4140, 4340	Slotting	1 x D	1 x D	4	300	.0006	.0008	.0009	.0011	.0012	.0015	.0018	.0021	.0024	.0030	.0036	.0048
		Peripheral - Rough	1.25 x D	.5 x D	4	375	.0008	.0009	.0011	.0013	.0015	.0019	.0023	.0026	.0030	.0038	.0045	.0060
			Finish	1.5 x D	.015 x D	4	450	.0008	.0010	.0012	.0014	.0017	.0021	.0025	.0029	.0033	.0041	.0050
	Tool & Die Steels <48 Rc A2, D2, H13, P20	Slotting	.75 x D	1 x D	4	300	.0006	.0008	.0009	.0011	.0012	.0015	.0018	.0021	.0024	.0030	.0036	.0048
		Peripheral - Rough	1.25 x D	.3 x D	4	375	.0007	.0009	.0011	.0013	.0015	.0018	.0022	.0025	.0029	.0036	.0044	.0058
			Finish	1.5 x D	.015 x D	4	450	.0008	.0009	.0011	.0013	.0015	.0019	.0023	.0026	.0030	.0038	.0045
M	Martensitic Stainless Steels 416, 410, 440C	Slotting	.75 x D	1 x D	4	300	.0006	.0008	.0009	.0011	.0012	.0015	.0018	.0021	.0024	.0030	.0036	.0048
		Peripheral - Rough	1.25 x D	.3 x D	4	375	.0007	.0009	.0011	.0013	.0015	.0018	.0022	.0025	.0029	.0036	.0044	.0058
			Finish	1.5 x D	.015 x D	4	450	.0008	.0009	.0011	.0013	.0015	.0019	.0023	.0026	.0030	.0038	.0045
	Austenitic Stainless Steels 303, 304, 316	Slotting	.75 x D	1 x D	4	275	.0007	.0008	.0010	.0011	.0013	.0016	.0020	.0023	.0026	.0033	.0039	.0052
		Peripheral - Rough	1.25 x D	.3 x D	4	325	.0008	.0010	.0012	.0014	.0016	.0020	.0024	.0028	.0032	.0040	.0048	.0064
			Finish	1.5 x D	.015 x D	4	400	.0008	.0010	.0012	.0014	.0017	.0021	.0025	.0029	.0033	.0041	.0050
	Precipitation Hardening Stainless Steels 17-4, 15-5, 13-8	Slotting	.5 x D	1 x D	4	250	.0005	.0006	.0008	.0009	.0010	.0013	.0015	.0018	.0020	.0025	.0030	.0040
		Peripheral - Rough	1.25 x D	.3 x D	4	300	.0006	.0008	.0009	.0011	.0013	.0016	.0019	.0022	.0025	.0031	.0038	.0050
			Finish	1.5 x D	.015 x D	4	375	.0007	.0008	.0010	.0011	.0013	.0016	.0020	.0023	.0026	.0033	.0039
S	Titanium Alloys 6AL - 4V	Slotting	.5 x D	1 x D	4	250	.0005	.0006	.0008	.0009	.0010	.0013	.0015	.0018	.0020	.0025	.0030	.0040
		Peripheral - Rough	1.25 x D	.3 x D	4	300	.0006	.0008	.0009	.0011	.0013	.0016	.0019	.0022	.0025	.0031	.0038	.0050
			Finish	1.5 x D	.015 x D	4	375	.0007	.0008	.0010	.0011	.0013	.0016	.0020	.0023	.0026	.0033	.0039
	High Temperature Alloys Inconel, Haynes, Stellite, Hastalloy	Slotting	.25 x D	1 x D	4	60	.0005	.0007	.0008	.0009	.0011	.0013	.0016	.0018	.0021	.0026	.0032	.0042
		Peripheral - Rough	1.25 x D	.25 x D	4	90	.0007	.0008	.0010	.0012	.0014	.0017	.0020	.0024	.0027	.0034	.0041	.0054
			Finish	1.5 x D	.01 x D	4	125	.0008	.0010	.0012	.0014	.0016	.0019	.0023	.0027	.0031	.0039	.0047

D = Tool Diameter

≈ Approximately Equals < Less Than
 ≤ Less Than or Equal To > Greater Than
 ≥ Greater Than or Equal To = Equals
 × Multiply

Common Machining Formulas

$$RPM = \frac{SFM \times 3.82}{D}$$

$$SFM = RPM \times D \times .262$$

$$IPM = RPM \times IPT \times Z$$

$$MRR = RDOC \times ADOC \times IPM$$

$$RPM = \frac{M/min \times 318.3}{D}$$

$$M/min = RPM \times D \times .00314$$

$$MMPM = RPM \times MMPT \times Z$$

$$MRR = RDOC \times ADOC \times MMPM$$

